


THER NCs-700-5-55

Patron

Passive Elektronik

Non-Silicone Thermal Conductive Pad



Non-Silicone Thermal Compound NCs-700 is made of non-silicon resin material. No low molecular siloxane volatilization and low total volatile gas, no electrical contact & pollution problems. NCs-700 is flexible and has great thermal conduction, Low com-pressive stress and high com-pressive characteristics can effectively reduce the stress load of components, so that the equipment only needs to bear less mechanical stress, and at the same time, it can have low thermal resistance and high thermal conductivity.

FEATURES

- / Thermal conductivity: 5.0 W/m*K
- / It's made by non-silicone resin materials
- / Low contact thermal resistance
- / With electrical insulation
- / Outstanding thermal conductivity
- / Applicable to optical and sensitive electric components

TYPICAL APPLICATION

- / HDDS
- / Optical appliance
- / 5G base station & infrastructure
- / EV electric vehicle

HOW TO ORDER

Patron THER NCs-700-5-55 XXX-YYY-ZZmm
XXX = width in mm
YYY = depth in mm
ZZ = thickness in mm

<https://www.patron-components.com/>

TYPICAL PROPERTIES

PROPERTY	NCs-700	TEST METHOD	UNIT
Color	Gray	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	3.2	ASTM D792	g/cm ³
Hardness	55	ASTM D2240	Shore OO
Tensile Strength	0.15	ASTM D412	Kgf/cm ²
Application temperature	-60~125	-	°C
Low molecular Siloxane (D3 to D20 total)	N.D	Gas Chromatography	%
Outgassing CVCN (wt%)	0.0061	-	-
ROHS & REACH	Compliant	-	-

COMPRESSION@1.0mm

Deflection @10 psi	16	ASTM D5470 modify	%
Deflection @20 psi	46	ASTM D5470 modify	%
Deflection @30 psi	68	ASTM D5470 modify	%

ELECTRICAL

Dielectric breakdown	8	ASTM D149	KV/mm
Surface resistivity	>10 ¹¹	ASTM D257	Ohm
Volume resistivity	>10 ¹⁰	ASTM D257	Ohm-m

THERMAL

Thermal conductivity	5.0	ASTM D5470	W/m*K
Thermal impedance@10 psi	0.312	ASTM D5470	°C-in ² / W
Thermal impedance@20 psi	0.208	ASTM D5470	°C-in ² / W
Thermal impedance@30 psi	0.132	ASTM D5470	°C-in ² / W

The chemical formula indicates that if Cyclic polydimethylsilox-ane (HO-[Si(CH₃)₂O]_n-H) is non-reaction, it's volatile anytime and everywhere. For example, when the electric products which has been put in a confined space, the volatile of low-molecular-weight silox-anes will makes the elecetic products uncontacted.

Thermal Resistance vs. Pressure vs. Deflection

